

NYCIL BC 2533

Driers, Additives & Thinners

PROPERTIES:

Solids
33 ± 2%

Clarity
Clear

Color (Gardner)
4 - 10

pH
6.5 - 7.5

BLOCKED CATALYSTS

BC 2533 is an amine blocked di- nonylnaphthalene di-sulphonic acid solution in alcoholic solvents.

COMPATIBILITY

HMMM resin:	Good
Epoxy resin (E.E.W. 450- 550):	Good

SOLUBILITY

n-Butanol:	Good
Isopropyl alcohol:	Good
Ester, Ketone:	Good

CURING SCHEDULES

Suitable for stoving finishes with stoving schedules ranging from 160°C for 20 minutes to 280°C for 50 - 70 seconds.

RECOMMENDATIONS FOR USE

To be used at 4 to 10 % on mass of melamine formaldehyde resin solids

This information provided in this Data Sheet is based on our own findings and we believe it to be reliable. However, it is only intended for general guidance of users and we do not accept any responsibility for the results obtained under different conditions of use.